

Chemische compatibiliteits-tabel voor SEAL STIC™

NB: De onderstaande chemische compatibiliteitstabel dient enkel als leidraad en is gebaseerd op gegevens die verkregen zijn van een onafhankelijke bron. Zij vertegenwoordigen geen actuele tests die door de fabrikant uitgevoerd zijn en zouden niet geïnterpreteerd moeten worden als garantie, bedoeld of geïmpliceerd als, geschikt of compatibel met SEAL STIC™ in contact met onderstaande stoffen. Vóór toepassing zal de gebruiker zelf bepalen of het product geschikt is voor het beoogde doel. De fabrikant en distributeur verwerpen alle aansprakelijkheid voor het gebruik en verkeerd gebruik van dit product en verwerpen tevens alle directe en indirecte incidentele of gevolgschade daarvan.

Resistentie Seal Stic putty - Chemisch Effect

- 1 – Uitstekend
- 2 – Goed
- 3 – Redelijk
- 4 – Niet aanbevolen

Superscript Detail

- A Bevredigend tot 22°C
- B Bevredigend tot 48°C

Acetaldehyde	1	Barium Nitrate	1 ^A	Copper Sulfate 5%	1 ^A	Hydrochloric Acid, Dry Gas	1
Acetamide	1	Barium Sulfate	3 ^A	Copper Sulfate >5%	1 ^A	Hydrochloric Acid 20%	2 ^A
Acetate Solvent	1	Barium Sulfide	2 ^A	Cream	1	Hydrochloric Acid 37%	1
Acetic Acid, Glacial	2 ^B	Beer	1 ^A	Cresols	1 ^A	Hydrocyanic Acid	1
Acetic Acid 20%	1	Beet Sugar Liquids	1 ^A	Cresylic Acid	1 ^A	Hydrofluoric Acid 20%	1
Acetic Acid 80%	3	Benzaldehyde	1 ^A	Cyanic Acid	1 ^A	Hydrofluoric Acid 50%	3 ^B
Acetic Acid	3	Benzoic Acid	1 ^A	Cyclohexane	1 ^A	Hydrofluoric Acid 75%	2 ^A
Acetic Anhydride	1	Benzol	1 ^A	Detergents	1 ^A	Hydrofluosulfuric Acid 20%	3 ^A
Acetone	4	Borax (Sodium Borate)	1 ^A	Dichlorethane	2 ^B	Hydrofluosulfuric Acid 100%	3 ^A
Acetyl Chloride (Dry)	1	Boric Acid	1 ^A	Diesel Fuel	1 ^A	Hydrogen Peroxide 10%	3 ^A
Acetylene	1	Brewery Slop	1	Diethylamine	1	Hydrogen Peroxide 30%	2
Acrylonitrile	1	Bromine	4	Diethylene Glycol	3	Hydrogen Peroxide 100%	1
Alcohols Amyl	4	Butadiene	1 ^A	Diphenyl Oxide	1	Hydrogen Sulfide (Aqua)	1
Benzyl	1 ^A	Butane	1 ^A	Dyes	1	Hydrogen Sulfide (Dry)	1
Butyl	1	Butanol (Butyl Alcohol)	4	Epsom Salts (Magnesium Sulfate)	1	Hydroxyacetic Acid 70%	1
Diacetone	1	Butter	1	Ethane	1 ^A	Ink	1
Ethyl	1 ^B	Buttermilk	1 ^A	Ethanolamine	1 ^A	Iodine	3
Hexyl	1	Butylene	1 ^A	Ether	1 ^A	Isotane	1
Isobutyl	1	Butylacetate	2 ^A	Ethyl Acetate	3 ^A	Isopropyl Acetate	1
Isopropyl	1	Butaric Acid	3 ^A	Ethyl Chloride	1 ^A	Isopropyl Ether	4
Methyl	2 ^A	Calcium Bisulfate	1	Ethyl Sulfate	1 ^A	Jet Fuel (JP#, -4, -5)	1
Octyl	1	Calcium Bisulfide	1	Ethylene Chloride	2 ^A	Kerosene	1
Propyl	1	Calcium Bisulfite	1 ^A	Ethylene Dichloride	3 ^A	Ketones	3
Aluminum Chloride 20%	1 ^A	Calcium Carbonate	1 ^A	Ethylene Glycol	3 ^A	Laquers	1
Aluminum Chloride	1 ^A	Calcium Chloride	1 ^A	Ethylene Oxide	1 ^A	Laquer Thinners	1
Aluminum Fluoride	2 ^A	Calcium Hydroxide	1 ^A	Fatty Acids	1 ^A	Lactic Acid	2 ^A
Aluminum Hydroxide	2 ^A	Calcium Hypochlorite	1 ^A	Ferric Chloride	1 ^A	Lard	2
Aluminum Potassium Sulfate 10%	1 ^A	Calcium Sulfate	1 ^A	Ferric Sulfate	1 ^A	Latex	1
Aluminum Potassium Sulfate 100%	1 ^A	Caigon	1	Ferrous Chloride	1 ^A	Lead Acetate	1
Aluminum Sulfate	1 ^A	Cane Juice	1	Ferrous Sulfate	1 ^A	Lead Sulfamate	1
Amines	1 ^A	Carbolic Acid (See Phenol)	3 ^A	Fluoboric Acid	1	Ligroin	1
Ammonia 10%	1 ^A	Carbon Bisulfide	1	Fluorine	4	Lime	1
Ammonia, Anhydrous	1	Carbon Dioxide	1 ^A	Fluosilicic Acid	3	Lubricants	1
Ammonia, Liquid	1 ^A	Carbon Dioxide (Dry)	1 ^A	Formaldehyde 40%	1 ^A	Magnesium Carbonate	1
Ammonia Nitrate	1	Carbon Dioxide (Wet)	1 ^A	Formaldehyde 100%	1	Magnesium Chloride	1
Ammonium Bifluoride	1 ^A	Carbon Disulfide	3 ^A	Formic Acid	3 ^A	Magnesium Hydroxide	1
Ammonium Carbonate	1 ^A	Carbon Monoxide	1 ^A	Freon 11	1	Magnesium Nitrate	1
Ammonium Casenite	1	Carbon Tetrachloride	1 ^A	Freon 12	1	Magnesium Oxide	1
Ammonium Chloride	1 ^A	Carbonated Water	1	Freon 22	1	Magnesium Sulfate	1
Ammonium Hydroxide	1 ^A	Carbonic Acid	2 ^A	Freon 113	1	Maleic Acid	1
Ammonium Nitrate	1 ^A	Catsup	1	Freon TF	1	Maleic Anhydride	1
Ammonium Oxalate	1	Chloroacetic Acid	3 ^A	Fruit Juice	1	Mash	1
Ammonium Persulfate	1 ^A	Chlorinated Glue	1	Fuel Oils	1 ^A	Mayonnaise	1
Ammonium Phosphate, Dibasic	1 ^A	Chlorine, Anhydrous Liquid	3 ^A	Furan Resin	1 ^A	Melamine	1
Ammonium Phosphate, Monobasic	1	Chlorine Water	1 ^A	Furfural	1 ^A	Mercuric Chloride (Dilute)	1
Ammonium Phosphate, Tribasic	1	Chlorobenzene (Mono)	3 ^B	Gasoline	1	Mercuric Cyanide	1
Ammonium Sulfate	1 ^A	Chloroform	3 ^A	Gelatin	2	Mercury	1
Ammonium Thiosulfate	1	Chlorosulfonic Acid	3 ^A	Glucose	2	Methanol (Methyl Alcohol)	2 ^A
Amyl Acetate	1 ^A	Chocolate Syrup	1	Glue, P.V.A.	1	Methyl Acetate	4
Amyl Alcohol	4	Chromic Acid 5%	2 ^A	Glycerin	1	Methyl Acrylate	1
Amyl Chloride	1 ^A	Chromic Acid 10%	3 ^A	Glycolic Acid	1	Methyl Acetone	3
Aniline	3 ^A	Chromic Acid 30%	3 ^A	Gold Monocyanide	1	Methyl Alcohol 10%	2 ^A
Anti-Freeze	1	Chromic Acid 50%	1	Grape Juice	1	Methyl Bromide	2
Aqua Regia (80% HCl, 20% HNO ₃)	4	Cider	1	Grease	1	Methyl Butyl Ketone	3
Arochlor 1248	1 ^A	Citric Acid	1 ^A	Heptane	1	Methyl Cellosolve	3
Aromatic Hydrocarbons	1	Citric Oils	1	Hexane	2	Methyl Dichloride	1
Arsenic Acid	1 ^A	Clorox (Bleach)	1	Honey	1	Methyl Ethyl Ketone	3 ^A
Asphalt	1	Coffee	1	Hydraulic Oil (Petro)	1	Methyl Isobutyl Ketone	3
Barium Carbonate	1 ^A	Copper Chloride	1	Hydraulic Oil (Synthetic)	1	Methyl Isopropyl Ketone	3
Barium Chloride	1 ^A	Copper Cyanide	2 ^A	Hydrazine	1	Methyl Methacrylate	1
Barium Cyanide	1	Copper Fluoborate	1	Hydrobromic Acid 20%	2 ^A	Methylamine	1
Barium Hydroxide	1 ^A	Copper Nitrate	1 ^A	Hydrobromic Acid 100%	4	Methylene Chloride	1
Milk	1	Phosphoric Acid (<40%)	1	Acid Fluoborate Bath R.T.	1	Sodium Sulfate	1
Molasses	1	Phosphoric Acid (>40%)	2	Alkaline Cyanide Bath R.T.	1	Sodium Sulfide	1
Mustard	1	Phosphoric Acid (Crude)	2	Potash	1	Sodium Sulfite	1
Naphtha	1	Photographic Developer	1	Potassium Bicarbonate	1	Sodium Tetraborate	1
Naphthalene	1	Picric Acid	1	Potassium Bromide	1	Sodium Thiosulfate (Hypo)	1
Nickel Chloride	1	Plating Solutions	1	Potassium Carbonate	1	Sorghum	1
Nickel Sulfate	1	Antimony Plating 130°F	2	Potassium Chlorate	1	Soy Sauce	1
Nitrating Acid (>15% H ₂ SO ₄)	4	Arsenic Plating 110°F	2	Potassium Chloride	1	Stannic Chloride	1

Nitric Acid (5-10%)	1 ^A	Brass Plating:		Potassium Chromate	3	Stannic Fluoborate	1
Nitric Acid (20%)	2 ^A	CU-CD Bronze Bath R.T.	2	Potassium Cyanide Solutions	1	Stannous Chloride	1
Nitric Acid (50%)	4	CU-SN Bronze Bath 160°F	3	Potassium Dichromate	3	Starch	1
Nitric Acid (Concentrated)	4	CU-ZN Bronze Bath 100°F	2	Potassium Ferrocyanide	1	Stearic Acid	2
Nitrobenzene	3 ^A	Cadmium Plating:		Potassium Hydroxide (Caustic	1	Stoddard Solvent	1
Oils: Aniline	1	Cyanide Bath 90°F	2	Potash)	1	Styrene	1
Anise	1	Fluoborate Bath 130°F	2	Potassium Nitrate	1	Sugar (Liquids)	1
Bay	1	Chromium Plating:		Potassium Permanganate	1	Sulfate (Liquors)	1
Bone	1	Chromic-Sulfuric Bath 130°F	3	Potassium Sulfate	1	Sulfur Chloride	3
Castor	1	Fluosilicate Bath 95°F	3	Propane (Liquified)	3	Sulfur Dioxide (Dry)	1 ^A
Cinnamon	1	Fluoride Bath 130°F	3	Propylene Glycol	1	Sulfur Trioxide (Dry)	1
Citric	1	Black Chrome Bath 115°F	3	Pyridine	1	Sulfuric Acid (<10%)	1 ^A
Clove	1	Barrel Chrome Bath 95 °F	3	Pyrogalllic Acid	1	Sulfuric Acid (10-75%)	3 ^A
Cocoa Nut	1	Copper Plating (Cyanide):		Rosins	1	Sulfuric Acid (75-100%)	1 ^A
Cod Liver	1	Copper Strike Bath 120°F	2	Rum	1	Sulfuric Acid (Hot Conc)	4
Corn	1	Rochelle Salt Bath 150°F	3	Rust Inhibitors	1	Sulfuric Acid (Cold Conc)	4
Cotton Seed	1 ^A	High Speed Bath 180°F	3	Salad Dressings	1	Sulfurous Acid	1
Creosote	1 ^A	Copper Plating (Acid):		Sea Water	1	Sulfuryl Chloride	1
Diesel Fuel (20, 30, 40, 50)	1 ^A	Copper Sulfate Bath R.T.	4	Shellac (Bleached)	1	Tallow	1
Fuel (1, 2, 3, 5A, 5B, 6)	1 ^A	Copper Fluoborate Bath	4	Shellac (Orange)	1	Tannic Acid	1
Ginger	1	120°F		Silicone	1	Tanning Liquors	1
Hydraulic (See Hydraulic)	1	Copper Plating (Misc):	2	Silver Bromide	1	Tartaric Acid	1
Lemon	1	Copper Pyrophosphate	2	Silver Nitrate	1	Tetrachloroethane	1
Linseed	1	Copper (Electroless)		Soap Solutions	1	Tetrahydrofuran	1
Mineral	1	Gold Plating:	4	Soda Ash (See Soda	1	Toluene (Toluol)	2 ^A
Olive	1	Cyanide 150°F	1	Carbonate)	1	Tomato Juice	1
Orange	1	Neutral 75°F	1	Sodium Acetate	1	Trichloroethane	1
Palm	1	Acid 75°F	1	Sodium Aluminate	1	Trichloroethylene	3 ^A
Peanut	1	Indium Sulfamate Plating R.T.		Sodium Bicarbonate	1	Trichloropropane	1
Peppermint	1	Iron Plating:	4	Sodium Bisulfate	1	Tricresylphosphate	1
Pine	1	Ferrous Chloride Bath 190°F	4	Sodium Bisulfite	3 ^A	Triethylamine	1
Rapeseed	1	Ferrous Sulfate Bath 150°F	4	Sodium Borate	1	Turpentine	2
Rosin	1	Ferrous AM Sulfate Bath	4	Sodium Carbonate	1	Urine	1
Sesame Seed	1	150°F	4	Sodium Chlorate	3	Varnish	1
Silicone	1	Sulfate Chloride Bath 160°F	1	Sodium Chloride	1	Vegetable Juice	1
Soybean	1	Fluoborate Bath 145°F	1	Sodium Chromate	1	Vinegar	1
Sperm	1	Sulfamate 140°F		Sodium Cyanide	1 ^B	Water, Acid, Mine	1
Tanning	1	Lead Fluoborate Plating	4	Sodium Fluoride	2 ^B	Water, Distilled	1
Turbine	1	Nickel Plating:	4	Sodium Hydroxide (20%)	1 ^A	Water, Fresh	1
Oleic Acid	1	Watts Type 115-160°F	1	Sodium Hydroxide (50%)	3	Water, Salt	1
Oleum 25%	4	High Chloride 130-160°F	1	Sodium Hydroxide (80%)	4	Weed Killers	1
Oleum 100%	4	Fluoborate 100-170°F	2	Sodium Hypochlorite (<20%)	3	Whey	1
Oxalic Acid (Cold)	1	Sulfamate 100-140°F	1	Sodium Hypochlorite (100%)	1	Whiskey and Wines	2
Paraffin	1	Electroless 200°F	1	Sodium Hyposulfate	1	White Liquor (Pulp Mill)	1
Pentane	1	Rhodium Plating 120°F	1	Sodium Metaphosphate	1	White Water (Paper Mill)	1
Perchloroethylene	4	Silver Plating 80-120°F	1	Sodium Metasilicate	2	Xylene	1
Petrolatum	1	Tin-Fluoborate Plating 100°F		Sodium Nitrate	3	Zinc Chloride	1
Phenol (10%)	3	Tin-Lead Plating 100°F	1	Sodium Perborate	1	Zinc Hydrosulfite	1
Phenol (Carbolic Acid)	3	Zinc Plating:	4	Sodium Peroxide	1	Zinc Sulfate	1
		Acid Chloride 14 °F		Sodium Polyphosphate			
		Acid Sulfate Bath 150°F		Sodium Silicate			

Opmerking:

Enkel Seal Stic staal epoxy putty is in de beoordeling meegenomen omdat dit product, in tegenstelling tot het Wrap Seal wikkerverband, bij een lekkage direct met het medium in contact komt.

SynTherm

T: +31 546 852328

F: +31 546 852340

E: info@syntherm.com

W: www.syntherm.com

Seal Stic & Wrap Seal

Pipe Repair Products

